



Spa Cover Fabric		Test Method
Material	12oz/sq. yard- Knife Coated PVC	
Construction	Woven - 1KDx1KD	Threads/sq. inch
Weight	12oz./yard	ASTMD751
Grab Tensile Stength	450MDx470CD	ASTMD751
Tongue Tear	128MDx127CD	ASTMD751
Trapezoid Tear	50MDx20CD	ASTMD751
Cold Crack	-40°C	ASTMD2136
Mildew Resistance	Level 0	ASTMG21
UV Resistence	Level 3.5-4.0astm2565	ASTMD4355
Chlorine Resistance	4.0+	AATCC162
Performance after 1200 hours UV Exposure		
Grab Tensile Stength	400MDx370CD	ASTMD751
Tongue Tear	88MDx192CD	ASTMD751
Trapezoid Tear	45MDx40CD	ASTMD751
Cold Crack	-40°C	ASTMD2136
Mildew Resistance	Level 0	ASTMG21
UV Resistence	Level 3.5-4.0astm2565	ASTMD4355
Chlorine Resistance	4.0+	AATCC162
1-833-MARKBRO (627-5276) - www.markbrousa.com		

**MarkBro Confidential **